

## Technical Data Sheet

### IMPULSE 75

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m <sup>2</sup>	75 +/- 3
Thickness	ISO 534	µm	102 +/- 4
Bulk	ISO 534		1,36
Moisture Content	ISO 287	%	4,4 +/- 0,5
Roughness	ISO 8791-2	Bendtsen ml/min	200 +/- 50
Whiteness	ISO 11475	CIE	161 +/- 3
Brightness D65	ISO 2470-2	%	107 +/- 2
Opacity	ISO 2471	%	90 +/- 2
Stiffness MD	ISO 2493	mN	85 +/- 10
Stiffness CD	ISO 2493	mN	45 +/- 5

#### Production sites:

The production mills operate in compliance with the following standards



#### Special Attributes:



References:  
Product is made taking into account requirements of DIN EN 12281  
Product made from ECF Pulp